

# MATERIAL TESTING LABORATORY

### **MILITARY ENGINEER SERVICES (MES)**

#### TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 252/2018-2019 (Steel). Copy No. : 02

Name of Client : GE(Navy) Patuakhali. Sample Specimen : Length 600 mm Dia 20mm

Ref Itr No : EinC/ 290 of 2017-2018/09/E-6 Dt. 25 March 2019. Sample Grade : 72.50

Project Name : EinC/ 290 of 2017-2018 Frog Mark
Date of Collection : Wednesday, 27 March, 2019

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	% (gauge El length) %		Elong % (g	Average Elongation % (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**	
1	0.787 20	0.791 20.101	0.4869 314.1593	1.674 2.491		38469.49 171.12	79001 545		48900.67 217.52	100423 692		20				
2	0.787 20	0.791 20.101	0.4869 314.1593	1.674 2.491	1.674 2.491	38570.65 171.57	79209 546	80328 554	49017.57 218.04	100663 694	101522 700	19.5		20		
3	0.787 20	0.791 20.101	0.4869 314.1593	1.674 2.491		40306.18 179.29	82773 571		50388.91 224.14	103479 713		19.5				

### **Cautions:**

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

## Observation on Specimen(if any):

1

Minimu	m Standard I	Requiremen	nts (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a)									
	6935-	2:1991(E)		ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)			
	N/mm2 or Mpa	N/mm2 or Mpa	%		psi (kg/cm2)	psi (kg/cm2)		Mpa (kg/cm2)	Mpa (kg/cm2)	10 mm	13,16,19 mm	22,25 mm	29,32,36 mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		100
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6

This is a computer genarated copy

No signature is required

: Baizid Steel 500 +

Note: [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian

Test Performed By

Vetted By