

MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No Name of Client Ref Itr No Project Name Date of Collection : 254/2018-2019 (Steel).

: GE(Navy) Patuakhali.

: EinC/ 294 of 2017-2018/06/E-6 Dt. 25 March 2019.

: EinC/294 of 2017-2018.

: Wednesday, 27 March, 2019

Copy No.
Sample Specimen
Sample Grade
Frog Mark

: 01

: Length 600 mm Dia 10mm

: 72.50

: Baizid Steel 500 +

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	% (g	(gauge El ngth) %		erage gation gauge gth)
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.394 10	0.399 10.123	0.1217 78.5398	0.425 0.632		10981.97 48.85	90211 622		13070.45 58.14	107367 740		13.5			
2	0.394 10	0.399 10.123	0.1217 78.5398	0.425 0.632	0.425 0.632	10844.83 48.24	89084 614	89478 617	12924.33 57.49	106166 732	106849 737	14.5		14	
3	0.394 10	0.399 10.123	0.1217 78.5398	0.425 0.632		10851.58 48.27	89140 615		13027.74 57.95	107016 738		13.5			

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu	m Standard I	Requiremen	nts (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a)										
6935-2:1991(E)				ASTM A 61	.5 M	ASTM A 615 M			ASTM A 615/A 615 M				This is a computer genarated copy	
Grade	Y/strength		Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum El	longation in 8"(2	203.2 mm)	GL (%)	No signature is required
	N/mm2 or Mpa	N/mm2 or Mpa	15276	3	psi	psi		Мра	Mpa	100000000000000000000000000000000000000	13,16,19 mm		29,32,36	
	ivipa	мра	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm		mm	mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian

Test Performed By

Vetted By