

MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES)

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

: 03 : 300/2018-2019(Steel) Copy No. Job No

Name of Client : GE(Air)Chattogram. Sample Specimen : Length 600 mm Dia 20mm

: 6005/22/E-6 Dt.30 April'2019 Sample Grade Ref Itr No : 60

Project Name : Airmen Training Institute. Frog Mark : SAS 400+ Date of Collection : Thursday, 02 May, 2019

Actual Dia Area Under Actual Unit Sample Nominal Average Yield or Yield or Illtimate Liltimate Average Flongation Average

No	Dia	Actual Dia	Test	Weight	Actual Unit Weight	Proof Load	Proof Strength	Yield or Proof Strength	Load	Strength	Ultimate Strength		gauge gth)	Elong % (g	gation gauge gth)
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.787 20	0.799 20.296	0.4869 314.1593	1.707 2.54		32253.49 143.47	66236 457		46234.42 205.66	94948 655		23			
2	0.787 20	0.799 20.296	0.4869 314.1593	1.707 2.54	1.707 2.54	32044.42 142.54	65807 454	67133 463	45850 203.95	94158 649	95976 662	20.5		23	
3	0.787 20	0.799 20.296	0.4869 314.1593	1.707 2.54		33773.21 150.23	69357 478		48120.58 214.05	98821 681		24			

Cautions:

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

Minimu	m Standard	Requiremen	its (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a)										
	6935-	2:1991(E)		ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M				
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)				
	N/mm2 or Mpa	N/mm2 or Mpa	%		psi (kg/cm2)	psi (kg/cm2)		Mpa (kg/cm2)	Mpa (kg/cm2)	10 mm	13,16,19 mm	22,25 mm	29,32,36 mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

This is a computer genarated copy No signature is required

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi]

Laboratory Technichian

Test Performed By

Vetted By