

MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES)

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 300/2018-2019(Steel) Copy No. : 02

Name of Client : GE(Air)Chattogram. Sample Specimen : Length 600 mm Dia 16mm

Ref Itr No : 6005/22/E-6 Dt.30 April'2019 Sample Grade : 60

Project Name : Airmen Training Institute. Frog Mark : SAS 400+ Date of Collection : Thursday, 02 May, 2019

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	% (g	gation gauge gth)	Elong % (g	rage gation gauge gth)
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.63 16	0.631 16.031	0.3116 201.0619	1.065 1.585		21833.55 97.12	70059 483		30475.24 135.56	97788 674		21			
2	0.63 16	0.631 16.031	0.3116 201.0619	1.065 1.585	1.065 1.585	21849.28 97.19	70109 483	70227 484	30027.87 133.57	96353 664	97196 670	19.5		19	
3	0.63 16	0.631 16.031	0.3116 201.0619	1.065 1.585		21975.18 97.75	70513 486		30369.58 135.09	97449 672		16.5			

Cautions:

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimum Standard Requirements (BDS/ISO				Minimum Standard Requirments(ASTM A615/A616M-96a)									
	6935-	2:1991(E)		ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)			
	N/mm2 or	CONTRACTOR OF THE PARTY OF THE	200	3	psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36
	Mpa	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm	42E 255	mm	mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6

This is a computer genarated copy

No signature is required

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi]

Laboratory Technichian

Test Performed By

Vetted By