

MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No Name of Client Ref Itr No Project Name Date of Collection : 319/18-19(Steel).

: GE (Navy) Dhaka.

: CEN/92 of 2018-2019/03/E-2.Dt 23 April 2019.

: CEN/92 of 2018-2019.

: Thursday, 9 May, 2019

Copy No. Sample Specimen Sample Grade Frog Mark

: Length 600 mm Dia 25mm

: 60

: 05

: RSRM 400 W.

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	Elong % (g leng	auge	Average Elongation % (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.984 25	0.994 25.244	0.7609 490.8739	2.64 3.929		53911.69 239.81	70857 488		77543.71 344.93	101917 703		29.5			
2	0.984 25	0.994 25.244	0.7609 490.8739	2.64 3.929	2.64 3.929	52007.55 231.34	68354 471	69637 480	76572.53 340.61	100640 694	101750 701	30		29	
3	0.984 25	0.994 25.244	0.7609 490.8739	2.64 3.929		53032.68 235.9	69701 481		78134.96 347.56	102694 708		28			

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E)				Minimum Standard Requirments(ASTM A615/A616M-96a) ASTM A 615 M ASTM A 615 M ASTM A 615/A 615 M									This is a computer genarated copy	
Grade	Grade Y/strength Ult.Str Elongation		Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Ult.Str Minimum Elongation in 8"(203.2 mm) GL (%)				No signature is required	
	N/mm2 or Mpa	N/mm2 or Mpa	%		psi (kg/cm2)	psi (kg/cm2)		Mpa (kg/cm2)	Mpa (kg/cm2)	10 mm	13,16,19 mm	22,25 mm	29,32,36 mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		110	
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian Test Performed By

Vetted By