

MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES)

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 319/18-19(Steel). Copy No. : 02

Name of Client : GE (Navy) Dhaka. Sample Specimen : Length 600 mm Dia 12mm

Ref Itr No : CEN/92 of 2018-2019/03/E-2.Dt 23 April 2019. Sample Grade : 60

Project Name : CEN/92 of 2018-2019. Frog Mark : RSRM 400 W. Date of Collection : Thursday, 9 May, 2019

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	% (g	gation gauge gth)	Elong % (g	rage gation gauge gth)
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.472 12	0.481 12.206	0.1753 113.0973	0.617 0.919		10997.71 48.92	62736 433		15039.79 66.9	85794 591		25			
2	0.472 12	0.481 12.206	0.1753 113.0973	0.617 0.919	0.617 0.919	11143.83 49.57	63570 438	63249 436	15125.22 67.28	86281 595	85837 592	25		24	
3	0.472 12	0.481 12.206	0.1753 113.0973	0.617 0.919		11121.35 49.47	63442 437		14976.84 66.62	85435 589		21.5			

Cautions:

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu	m Standard	Requiremen	its (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a)										
6935-2:1991(E)				ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M				
Grade	Y/strength Ult.Str		Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum El	mum Elongation in 8"(203.2 mm) GL (%)			
	N/mm2 or Mpa	N/mm2 or Mpa	%		psi (kg/cm2)	psi (kg/cm2)		Mpa (kg/cm2)	Mpa (kg/cm2)	10 mm	13,16,19 mm	22,25 mm	29,32,36 mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

This is a computer genarated copy

No signature is required

Note: [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian

Test Performed By

Vetted By