

# MATERIAL TESTING LABORATORY

### MILITARY ENGINEER SERVICES (MES)

### TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 319/18-19(Steel). Copy No. : 01

Name of Client : GE (Navy) Dhaka. Sample Specimen : Length 600 mm Dia 10mm

Ref Itr No : CEN/92 of 2018-2019/03/E-2.Dt 23 April 2019. Sample Grade : 60

Project Name : CEN/92 of 2018-2019. Frog Mark : RSRM 400 W. Date of Collection : Thursday, 9 May, 2019

Actual Dia Area Under Yield or Yield or Elongation Sample Nominal Actual Unit Average Average Ultimate Ultimate Average Average No Test Weight Actual Ŭnit **Proof Load** Proof Yield or Load Ultimate Elongation Dia Strength % (gauge Weight Proof length) Strength Strength % (gauge Strength length) 8inch 5d\*\* 8inch | 5d\*\* inch inch lb/ft lb/ft lb lb sq.inch psi psi psi psi mm mm sq.mm kg/m kg/m kn Mpa Mpa kn Mpa Mpa 10372.73 22.5 1 0.394 0.397 0.1217 0.422 8147.11 66924 85206 10 10.094 78.5398 0.628 36.24 461 46.14 587 2 8124.63 10566.07 21.5 22 0.394 0.397 0.1217 0.422 0.422 66739 66450 86794 86031 10.094 78.5398 0.628 460 593 10 0.628 36.14 458 47 598 3 21.5 0.394 0.397 0.1217 0.422 7996.49 65687 10480.64 86093 10 10.094 78.5398 0.628 35.57 453 46.62 594

#### **Cautions:**

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

## **Observation on Specimen(if any):**

1.

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E)				Minimum Standard Requirments(ASTM A615/A616M-96a)									
				ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)			
	N/mm2 or	Control of the Contro	32.8		psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36
	Mpa	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm	A 250	mm	mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		**
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	1344	7	7	6

This is a computer genarated copy

No signature is required

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi]

Laboratory Technichian

Test Performed By

Vetted By