

## MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

## TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No Name of Client Ref Itr No Project Name Date of Collection : 321/18-19(Steel).

: GE (Navy) Dhaka.

: CEN/93 of 2018-2019/03/E-2.Dt 23 April 2019.

: CEN/93 of 2018-2019.

: Thursday, 9 May, 2019

Copy No. Sample Specimen Sample Grade Frog Mark

: Length 600 mm Dia 12mm

: 60

: 02

: RSRM 400 W.

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	Elong % (g leng	auge		
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.472 12	0.478 12.149	0.1753 113.0973	0.612 0.91		11465.31 51	65404 451		15469.18 68.81	88244 608		22.5			
2	0.472 12	0.478 12.149	0.1753 113.0973	0.612 0.91	0.612 0.91	10824.6 48.15	61749 426	63715 439	14567.69 64.8	83101 573	86081 593	21.5		22	
3	0.472 12	0.478 12.149	0.1753 113.0973	0.612 0.91		11218.02 49.9	63993 441		15233.13 67.76	86897 599		20.5			

## **Cautions:**

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

## **Observation on Specimen(if any):**

1.

Minimu		Requiremer 2:1991(E)	nts <mark>(BDS/I</mark> SO	Minimum Standard Requirments(ASTM A615/A616M-96a) ASTM A 615 M ASTM A 615 M ASTM A 615/A 615 M										This is a computer genarated copy
Grade	Grade Y/strength Ult.Str Elongation		Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)				No signature is required	
	N/mm2 or Mpa	N/mm2 or Mpa	%		psi (kg/cm2)	psi (kg/cm2)		Mpa (kg/cm2)	Mpa (kg/cm2)	10 mm	13,16,19 mm	22,25 mm	29,32,36 mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		110	
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian Test Performed By

Vetted By