

# MATERIAL TESTING LABORATORY

### **MILITARY ENGINEER SERVICES (MES)**

#### TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 30/19-20(Steel) Copy No. : 1

Name of Client : AGE(Army) Momenshahi. Sample Specimen : Length 600 mm Dia 10mm

Ref Itr No : EinC/456 of 2018-2019/07/E-6 Dt. 17 July' 2019. Sample Grade : 72.00

Project Name : EinC/456 of 2018-2019.
Date of Collection : Thursday, 18 July, 2019

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	% (g	gation gauge gth)	Average Elongation % (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.394 10	0.395 10.026	0.1217 78.5398	0.417 0.62		10102.96 44.94	82990 572		12321.84 54.81	101217 698		14.5			
2	0.394 10	0.395 10.026	0.1217 78.5398	0.417 0.62	0.417 0.62	10566.07 47	86794 598	83754 577	12557.89 55.86	103156 711	101057 697	13		14	
3	0.394 10	0.395 10.026	0.1217 78.5398	0.417 0.62	•	9918.62 44.12	81476 562		12027.34 53.5	98798 681		14			

### **Cautions:**

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

## **Observation on Specimen(if any):**

1.

Minimu	m Standard	Requiremer	nts (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a)										
	6935-	2:1991(E)		ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M				
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (			GL (%)	
	N/mm2 or	CONTRACTOR OF THE PERSON NAMED IN	3338		psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36	
	Mpa	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm	200 000 A	mm	mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

This is a computer genarated copy

No signature is required

Note: [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian

Test Performed By

Frog Mark

Vetted By

: Purbachal 500W