



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES (MES)

TEST RESULTS FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 90/19-20(Con).
Name of Client : AGE (Air) shamshernagar. Copy No. : 01
Ref Itr No : CE(Air)/51 of 2018-2019/17/E-6.Dt 28 July 2019. Sample Specimen : HT 200mm (8"), Dia 100mm (4")
Project Name : CE(Air)/51 of 2018-2019. Type of Aggregate : Brick
Status of Sample : 2nd floor roof slab. Brand & Type of Cement : Seven ring cement opc.
Date of Collection : Monday, 29 July, 2019 Proportion of Mixture : 1:2:4
Test Standard : ASTM/BS Desired Design Strength : 1950 psi.

Ser No	Date of Casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs.)	Crushing Strength (psi)	Average Crushing Strength (psi)	Type of Failure
1	25-Jul-19 (7 days)	01-Aug-19	12.17	34563	2840	2619	Aggregate/ Mortar or Both Failure
2			12.17	34292	2818		
3			12.17	26767	2199		

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the samples to be tested.
2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

- 1.

Laboratory Technichian

Test Performed By

Vetted By

This is a computer generated copy

No signature is required

Permissible Value:

- 1.

Note :[1 Mpa = 145 Psi, 1 kg/cm² = 14.223 psi]