

## MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

## TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No Name of Client Ref Itr No Project Name Date of Collection

: 88/2019-2020(Steel) : AGE(Army) Momenshahi. : CEA/392 of 2018-2019/12/E-6 Dt.05 Aug'2019 : CEA/392 of 2018-2019

: Tuesday, 06 August, 2019

Copy No.
Sample Specimen
Sample Grade
Frog Mark

: 03

: Length 600 mm Dia 16mm

: 60

: Purbachal400

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	% (g	gation gauge gth)	Elong	auge
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.63 16	0.635 16.124	0.3116 201.0619	1.077 1.603		23400.47 104.09	75087 518		29742.36 132.3	95436 658		18.5			
2	0.63 16	0.635 16.124	0.3116 201.0619	1.077 1.603	1.077 1.603	22566.43 100.38	72410 499	72449 499	28159.7 125.26	90358 623	92193 636	17.5		18	
3	0.63 16	0.635 16.124	0.3116 201.0619	1.077 1.603		21768.35 96.83	69850 482		28292.34 125.85	90784 626		17			

## **Cautions:**

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

## **Observation on Specimen(if any):**

1.

Minimu		Requiremer 2:1991(E)	nts (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a) ASTM A 615 M ASTM A 615 M ASTM A 615/A 615 M								This is a computer genarated copy		
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum El	ongation in 8"(2	203.2 mm)	GL (%)	No signature is required
	N/mm2 or Mpa	N/mm2 or Mpa	%		psi (kg/cm2)	psi (kg/cm2)		Mpa (kg/cm2)	Mpa (kg/cm2)	10 mm	13,16,19 mm	22,25 mm	29,32,36 mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		110	
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian Test Performed By

Vetted By