

MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES)

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 144/19-20(Steel). Copy No. : 03

Name of Client : GE (Air) Chattogram. Sample Specimen : Length 600 mm Dia 16mm

Ref Itr No : 6005/47/12/E-6 Dt. 05 September'2019. Sample Grade : 60

Project Name : EinC/193 of 2017-2018. Frog Mark : AKS 500W

Date of Collection : Wednesday, 11 September, 2019

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	Elong % (g leng		Average Elongation % (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.63 8	0.631 16.036	0.3116 201.0619	1.066 1.586		26493.86 117.85	85013 586		32010.7 142.39	102715 708		18.5			
2	0.63 8	0.631 16.036	0.3116 201.0619	1.066 1.586	1.066 1.586	26860.3 119.48	86188 594	85905 592	32658.15 145.27	104792 722	104232 719	19.5		19	
3	0.63 8	0.631 16.036	0.3116 201.0619	1.066 1.586		26961.46 119.93	86513 596		32781.79 145.82	105189 725		18			

Cautions:

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E)				Minimum Standard Requirments(ASTM A615/A616M-96a)									
				ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%			GL (%)
	N/mm2 or	Control of the Contro	25-26		psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36
	Mpa	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm		mm	mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	:**	7	7	6

This is a computer genarated copy

No signature is required

Note: [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian

Test Performed By

Vetted By