

MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES)

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 145/19-20(Steel). Copy No. : 01

Name of Client : GE (Air) Chattogram. Sample Specimen : Length 600 mm Dia 10mm

Ref Itr No : 6005/43/20/E-6 Dt. 05 September'2019. Sample Grade : 60

Project Name : EinC/225 of 2017-2018. Sample Grade : AKS 500W

Date of Collection : Wednesday, 11 September, 2019

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	Elong % (g leng		Elong	auge
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.394 10	0.396 10.052	0.1217 78.5398	0.419 0.623		11049.41 49.15	90765 626		12825.41 57.05	105354 726		17.5			
2	0.394 10	0.396 10.052	0.1217 78.5398	0.419 0.623	0.419 0.623	10885.3 48.42	89417 616	90605 625	12717.5 56.57	104467 720	89995 620	15.5		16	
3	0.394 10	0.396 10.052	0.1217 78.5398	0.419 0.623		11155.07 49.62	91633 632		7324.31 32.58	60165 415		15.5			

Cautions:

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimum Standard Requirements (BDS/ISO				Minimum Standard Requirments(ASTM A615/A616M-96a)										
	6935-2	2:1991(E)		ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M				
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength Ult.Str Minimum Elongatio				in 8"(203.2 mm) GL (%)		
	N/mm2 or	Carl Carlotter	252.00		psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36	
	Мра	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm		mm	mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

This is a computer genarated copy

No signature is required

Note: [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laborator

Laboratory Technichian

Test Performed By

Vetted By