

MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES)

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 145/19-20(Steel). Copy No. : 04

Name of Client : GE (Air) Chattogram. : Length 600 mm Dia 20mm

Ref Itr No : 6005/43/20/E-6 Dt. 05 September'2019. Sample Grade : 60

Project Name : EinC/225 of 2017-2018. Frog Mark : AKS 500W

Date of Collection : Wednesday, 11 September, 2019

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	% (g	gation gauge gth)	Elong % (g	erage gation gauge gth)
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.787 32	0.791 20.101	0.4869 314.1593	1.674 2.491		42462.11 188.88	87201 601		51049.85 227.08	104837 723		21			
2	0.787 32	0.791 20.101	0.4869 314.1593	1.674 2.491	1.674 2.491	41511.17 184.65	85248 588	86065 593	50256.28 223.55	103207 712	103750 715	22.5		22	
3	0.787 32	0.791 20.101	0.4869 314.1593	1.674 2.491		41753.96 185.73	85746 591		50256.28 223.55	103207 712		21.5			

Cautions:

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E)				Minimum Standard Requirments(ASTM A615/A616M-96a)									
				ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%			GL (%)
	N/mm2 or	CONTRACTOR OF THE PARTY OF THE	32.8		psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36
	Mpa	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm	2	mm	mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6

This is a computer genarated copy

No signature is required

Note: [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laborat

Laboratory Technichian

Test Performed By

Vetted By