



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICES (MES)

TEST RESULTS FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No	: 296/19-20(Con).	Copy No.	: 02
Name of Client	: AGE (Army) Momenshahi.	Sample Specimen	: HT 200mm (8"), Dia 100mm (4")
Ref Itr No	: EinC/456 of 2018-2019/08/E-6 Dt 01 Oct'2019.	Type of Aggregate	: Stone
Project Name	: EinC/456 of 2018-2019	Brand & Type of Cement	: Elephant opc.
Status of Sample	: Grade beam & column	Proportion of Mixture	: 1:1.5:3
Date of Collection	: Wednesday, 02 October, 2019	Desired Design Strength	: 3500 psi
Test Standard	: <u>ASTM/BS</u>		

Ser No	Date of Casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs.)	Crushing Strength (psi)	Average Crushing Strength (psi)	Type of Failure
1	26-Sep-19 (28 days)	24-Oct-19	12.17	30330	2492	2424	Aggregate/ Morter or Both Failure
2			12.17	31114	2557		
3			12.17	27052	2223		

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the samples to be tested.
2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1. As the strength is below the desired design strength, so nec. measures to be taken as per particular specifications of contract.

Laboratory Technichian

Test Performed By

Vetted By

This is a computer generated copy

No signature is required

Permissible Value:

1.

Note : [1 Mpa = 145 Psi, 1 kg/cm² = 14.223 psi]