

# MATERIAL TESTING LABORATORY

### **MILITARY ENGINEER SERVICES (MES)**

#### TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 239/19-20(Steel). Copy No. : 05

Name of Client : GE (Navy) South, Chattogram. : Length 600 mm Dia 25mm

Ref Itr No : CEN/343 of 2018-2019/14/E-6 Dt.19 Sept'2019. Sample Grade : 60

Project Name : CEN/343 of 2018-2019 Frog Mark : AKS 500W

Date of Collection : Thursday, 07 November, 2019

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	% (g	gation gauge gth)	Elong % (g	erage gation gauge gth)
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.984 25	0.988 25.083	0.7609 490.8739	2.607 3.879		65421.96 291.01	85985 593		76887.27 342.01	101054 697		22.5			
2	0.984 25	0.988 25.083	0.7609 490.8739	2.607 3.879	2.607 3.879	64918.38 288.77	85323 588	84287 581	76864.79 341.91	101024 696	100106 690	22.5		23	
3	0.984 25	0.988 25.083	0.7609 490.8739	2.607 3.879		62049.81 276.01	81553 562		74747.08 332.49	98241 677		24			

### **Cautions:**

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

## **Observation on Specimen(if any):**

1.

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E)				Minimum Standard Requirments(ASTM A615/A616M-96a)									
				ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
Grade	Y/strength	Ult.Str	Elongation	Grade	Grade Y/strength Ult.Str Grade Y/strength Ult.			Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)				
	N/mm2 or	Contraction of the Contraction o	70275		psi	psi		Мра	Mpa	10	13,16,19 mm	22,25	29,32,36
	Mpa	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm		mm	mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6

This is a computer genarated copy

No signature is required

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi]

Laboratory Technichian

Test Performed By

Vetted By