

MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No Name of Client Ref Itr No Project Name Date of Collection

: CEN/343 of 2018-2019/14/E-6 Dt.19 Sept'2019. : CEN/343 of 2018-2019

: GE (Navy) South, Chattogram.

: 239/19-20(Steel).

: Thursday, 07 November, 2019

: 04 Copy No. Sample Specimen Sample Grade : 60 Frog Mark : AKS 500W

: Length 600 mm Dia 20mm

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	Elong % (g leng	auge	Average Elongation % (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.787 20	0.791 20.095	0.4869 314.1593	1.673 2.49		42716.15 190.01	87722 605		51240.94 227.93	105229 725		22			
2	0.787 20	0.791 20.095	0.4869 314.1593	1.673 2.49	1.673 2.49	41983.27 186.75	86217 594	86460 596	50555.27 224.88	103821 716	104295 719	21.5		22	
3	0.787 20	0.791 20.095	0.4869 314.1593	1.673 2.49		41605.59 185.07	85442 589		50562.02 224.91	103835 716		22.5			

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu	Minimum Standard Requirements (BDS/ISO			Minimum Standard Requirments(ASTM A615/A616M-96a)										
6935-2:1991(E)			ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M				This is a computer genarated copy	
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength Ult.Str		Minimum Elongation in 8"(203.2 mm) GL (%)			GL (%)	No signature is required
	N/mm2 or	Contraction of the second second	22-25		psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36	
	Мра	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm		mm	mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note :[1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian Test Performed By

Vetted By