

MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No Name of Client Ref Itr No Project Name Date of Collection

: GE (Navy) Dhaka. : 2000/Test/134/E-2 Dt. 29 Oct'2019. : Not Mentioned

: 233/19-20(Steel)

: Thursday, 31 October, 2019

Copy No.	: 02
Sample Specimen	: Ler
Sample Grade	: 60
Frog Mark	: AS

Length 600 mm Dia 12mm

ASBRM 400

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	% (gauge Elo length) %		Elong % (g	erage gation gauge gth)
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.472 12	0.477 12.126	0.1753 113.0973	0.609 0.907		9977.07 44.38	56914 392		15015.06 66.79	85653 590		20			
2	0.472 12	0.477 12.126	0.1753 113.0973	0.609 0.907	0.609 0.907	10561.57 46.98	60248 415	60509 417	16332.45 72.65	93168 642	91193 629	21.5		21	
3	0.472 12	0.477 12.126	0.1753 113.0973	0.609 0.907		11283.21 50.19	64365 444		16611.21 73.89	94758 653		21.5			

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu	Minimum Standard Requirements (BDS/ISO Minimum Standard Requirments(ASTM A615/A616M-96a)													
6935-2:1991(E)			ASTM A 615 M				ASTM A 61	5 M	ASTM A 615/A 615 M				This is a computer genarated copy	
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) (GL (%)	No signature is required	
	N/mm2 or	Contraction of the second	22.35	3	psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36	
	Мра	Мра	%	· · · · · · · · · · · · · · · · · · ·	(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm		mm	mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian

Test Performed By

Vetted By