

MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No Name of Client Ref Itr No Project Name Date of Collection

: GE (Navy) Dhaka. : 2000/Test/134/E-2 Dt. 29 Oct'2019. : Not Mentioned

: 233/19-20(Steel)

: Thursday, 31 October, 2019

Copy No.	: 04
Sample Specimen	: Ler
Sample Grade	: 60
Frog Mark	: AS

Length 600 mm Dia 20mm

60

ASBRM 400

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength		gation gauge gth)	auge Elongatio	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.787 20	0.795 20.187	0.4869 314.1593	1.688 2.513		32761.56 145.73	67280 464		51818.71 230.5	106416 734		23.5			
2	0.787 20	0.795 20.187	0.4869 314.1593	1.688 2.513	1.688 2.513	33507.93 149.05	68812 474	68312 471	52250.34 232.42	107302 740	106900 737	25		24	
3	0.787 20	0.795 20.187	0.4869 314.1593	1.688 2.513		33523.67 149.12	68845 475		52095.22 231.73	106983 738		23.5			

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu	Minimum Standard Requirements (BDS/ISO Minimum Standard Requirments(ASTM A615/A616M-96a)													
6935-2:1991(E)				ASTM A 61		ASTM A 61	5 M	ASTM A 615/A 615 M				This is a computer genarated copy		
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (GL (%)	No signature is required	
	N/mm2 or	Contraction of the second second	255.25		psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36	
	Мра	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm		mm	mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note :[1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian

Test Performed By

Vetted By