

MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No Name of Client Ref Itr No Project Name Date of Collection

: AGE (Army) Momenshahi. : CEA/659 of 2018-2019/26/E-6.Dt 07 Oct' 2019. : CEA/659 of 2018-2019.

: 375/19-20(Steel).

: Thursday, 30 January, 2020

Copy No.
Sample Specimen
Sample Grade
Frog Mark

: 01

: Length 600 mm Dia 10mm

: 60

: Purbachal 400

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	% (g	gauge Elong ngth) % (g		rage gation auge gth)
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.394 10	0.401 10.191	0.1217 78.5398	0.43 0.64		8974.42 39.92	73720 508		12524.17 55.71	102879 709		21.5			
2	0.394 10	0.401 10.191	0.1217 78.5398	0.43 0.64	0.43 0.64	8868.75 39.45	72852 502	73905 509	12481.45 55.52	102528 707	103532 714	20		20	
3	0.394 10	0.401 10.191	0.1217 78.5398	0.43 0.64		9147.52 40.69	75142 518		12805.18 56.96	105187 725		19			

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu	m Standard I	Requiremen	nts (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a)										
6935-2:1991(E)				ASTM A 61	.5 M	ASTM A 615 M			ASTM A 615/A 615 M				This is a computer genarated copy	
Grade	Y/strength		Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum El	longation in 8"(2	203.2 mm)	GL (%)	No signature is required
	N/mm2 or Mpa	N/mm2 or Mpa	35275	3	psi	psi		Мра	Mpa	100000000000000000000000000000000000000	13,16,19 mm		29,32,36	
	ivipa	мра	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm		mm	mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note :[1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian Test Performed By

Vetted By