

MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

Page No. 1238

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No Name of Client Ref Itr No Project Name Date of Collection

: AGE (Army) Momenshahi. : CEA/659 of 2018-2019/26/E-6.Dt 07 Oct' 2019. : CEA/659 of 2018-2019.

: 375/19-20(Steel).

: Thursday, 30 January, 2020

Copy No. Sample Specimen Sample Grade Frog Mark

: 03 : Length 600 mm Dia 20mm

: 60

: Purbachal 400

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	Elong % (g leng		Elong % (g	erage gation gauge gth)
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.787 20	0.793 20.137	0.4869 314.1593	1.68 2.5		33609.1 149.5	69020 476		48349.89 215.07	99292 685		17.5			
2	0.787 20	0.793 20.137	0.4869 314.1593	1.68 2.5	1.68 2.5	34220.58 152.22	70276 484	69356 478	48738.81 216.8	100091 690	99629 687	17.5		20	
3	0.787 20	0.793 20.137	0.4869 314.1593	1.68 2.5		33487.7 148.96	68771 474		48453.3 215.53	99504 686		25.5			

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu	Minimum Standard Requirements (BDS/ISO				М									
6935-2:1991(E)			ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M				This is a computer genarated copy	
Grade	Y/strength		Elongation	Grade Y/strength Ult.Str Grade Y/st					Ult.Str Minimum Elongation in 8"(203.2 mm) GL (%)				No signature is required	
	N/mm2 or Mpa	N/mm2 or Mpa	%	8	psi	psi		Mpa	Mpa		13,16,19 mm		29,32,36	
	wipa	wipa	70		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm		mm	mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note :[1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian

Test Performed By

Vetted By