

MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES)

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

: 411/19-20(Steel). Copy No. : 04 Job No

Name of Client : GE (Air) Chattogram. Sample Specimen : Length 600 mm Dia 20mm

Sample Grade : 60 Ref Itr No : 6005/62/14/E-6 Dt. 01 Mar'2020.

Project Name : CE (Air)/76 of 2018-2019. Frog Mark : GPH 500+ Date of Collection : Thursday, 05 March, 2020

Actual Dia | Area Under | Actual Unit | Yield or Average Sample Nominal Yield or Average Ultimate Ultimate Average Elongation Average

No	Dia		Test	Weight	Actual Unit Weight	Proof Load	Proof Strength	Yield or Proof Strength	Load	Strength	Ultimate Strength	% (g len	auge gth)		gation auge gth)
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.787 20	0.787 20.002	0.4869 314.1593	1.658 2.467		38314.37 170.43	78683 542		48352.13 215.08	99297 685		21.5			
2	0.787 20	0.787 20.002	0.4869 314.1593	1.658 2.467	1.658 2.467	40951.39 182.16	84098 580	80780 557	50085.42 222.79	102856 709	100600 694	19		20	
3	0.787 20	0.787 20.002	0.4869 314.1593	1.658 2.467		38741.51 172.33	79560 548		48522.99 215.84	99647 687		20.5			

Cautions:

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu	m Standard	Requiremen	nts (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a)										
	6935-	2:1991(E)		ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M				
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	trength Ult.Str Grade Y/strength Ult				Minimum Elongation in 8"(203.2 mm) GL (%)				
	N/mm2 or	Contraction of the Contraction o	70275		psi	psi		Мра	Mpa	10	13,16,19 mm	22,25	29,32,36	
	Mpa	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm		mm	mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

This is a computer genarated copy No signature is required

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi]

Laboratory Technichian

Test Performed By

Vetted By