

# MATERIAL TESTING LABORATORY

### **MILITARY ENGINEER SERVICES (MES)**

#### TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 411/19-20(Steel). Copy No. : 02

Name of Client : GE (Air) Chattogram. Sample Specimen : Length 600 mm Dia 12mm

Ref Itr No : 6005/62/14/E-6 Dt. 01 Mar'2020. Sample Grade : 60

Project Name : CE (Air)/76 of 2018-2019. Frog Mark : GPH 500+ Date of Collection : Thursday, 05 March, 2020

Area Under Actual Dia Yield or Yield or Elongation Sample Nominal Actual Unit Average Average Ultimate Ultimate Average Average No Test Weight Actual Ŭnit **Proof Load** Proof Yield or Load Ultimate % (gauge Elongation Dia Strength Weight Proof length) Strength Strength % (gauge Strength length) 8inch | 5d\*\* 8inch | 5d\*\* inch inch lb/ft lb/ft lb lb sq.inch psi psi psi psi mm mm sq.mm kg/m kg/m kn Mpa Mpa kn Mpa Мра 1 0.472 0.472 0.1753 0.597 14943.12 85243 18193.87 103787 16.5 12 12 113.0973 0.888 66.47 588 80.93 716 2 0.472 0.472 0.597 15019.56 85679 18083.72 103158 102072 17 0.1753 0.597 84418 17 113.0973 0.888 0.888 591 582 704 12 12 66.81 80.44 711 3 0.472 0.472 17402.54 99272 17.5 0.1753 0.597 14432.8 82332 12 12 113.0973 0.888 64.2 568 77.41 684

# **Cautions:**

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

## **Observation on Specimen(if any):**

1.

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E)				Minimum Standard Requirments(ASTM A615/A616M-96a)									
				ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)			GL (%)
	N/mm2 or Mpa	N/mm2 or Mpa	%		psi (kg/cm2)	psi (kg/cm2)		Mpa (kg/cm2)	Mpa (kg/cm2)	10 mm	13,16,19 mm	22,25 mm	29,32,36 mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		(100)
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6

This is a computer genarated copy

No signature is required

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi]

Laboratory Technichian

Test Performed By

Vetted By