

# MATERIAL TESTING LABORATORY

## **MILITARY ENGINEER SERVICES (MES)**

#### TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 03/2020-2021(Steel). Copy No. : 02

Name of Client : GE (Army) Barishal. Sample Specimen : Length 600 mm Dia 12mm

Ref Itr No : 6000/45/E-6 Dt. 12 July'2020. Sample Grade : 60

Project Name : Not mentioned.

Date of Collection : Tuesday, 14 July, 2020

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	% (g	gation Aver gauge Elong ngth) % (ga leng		gation auge
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.472 12	0.477 12.106	0.1753 113.0973	0.607 0.904		13272.78 59.04	75714 522		20012.59 89.02	114161 787		21.5			
2	0.472 12	0.477 12.106	0.1753 113.0973	0.607 0.904	0.607 0.904	13295.26 59.14	75843 523	75962 524	20012.59 89.02	114161 787	114166 787	20		21	
3	0.472 12	0.477 12.106	0.1753 113 0973	0.607 0.904		13380.69 59.52	76330 526		20014.83 89.03	114174 787		20.5			

### **Cautions:**

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

## **Observation on Specimen(if any):**

1.

Minimu	m Standard	Requiremer	nts (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a)										
	6935-	2:1991(E)		ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M				
Grade	Y/strength	Ult.Str	Elongation	ongation Grade Y/strength Ult.Str Grade				Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)				
	N/mm2 or	CONTRACTOR OF THE PARTY OF THE	3338		psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36	
	Mpa	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm	400 000 A	mm	mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

This is a computer genarated copy

No signature is required

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi]

Laboratory Technichian

Test Performed By

Frog Mark

Vetted By

: Rani 420 DWR