

MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No Name of Client Ref Itr No Project Name Date of Collection

: GE (Army) Barishal. : 6000/45/E-6 Dt. 12 July'2020. : Not mentioned.

: 03/2020-2021(Steel).

: Tuesday, 14 July, 2020

Copy No. Sample Specimen Sample Grade Frog Mark

: Length 600 mm Dia 10mm

: 60

: 01

: Rani 420 DWR

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	Elongation % (gauge length)		Elong % (g	erage gation gauge gth)
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.394 10	0.396 10.052	0.1217 78.5398	0.419 0.623		8578.75 38.16	70470 486		14731.8 65.53	121014 834		17.5			
2	0.394 10	0.396 10.052	0.1217 78.5398	0.419 0.623	0.419 0.623	8810.3 39.19	72372 499	71104 490	14605.91 64.97	119979 827	120250 829	16.5		17	
3	0.394 10	0.396 10.052	0.1217 78.5398	0.419 0.623		8578.75 38.16	70470 486		14578.93 64.85	119758 826		16.5			

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu		Requiremer 2:1991(E)	nts (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a) ASTM A 615 M ASTM A 615 M ASTM A 615/A 615 M									This is a computer genarated copy	
Grade Y/strength Ult.Str Elongation		Grade	Y/strength	Ult.Str	Grade	Y/strength		Minimum Elongation in 8"(203.2 mm) GL (%)			GL (%)	No signature is required		
	N/mm2 or Mpa	N/mm2 or Mpa	%		psi (kg/cm2)	psi (kg/cm2)		Mpa (kg/cm2)	Mpa (kg/cm2)	10 mm	13,16,19 mm	22,25 mm	29,32,36 mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		×.	
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian Test Performed By

Vetted By