Copy No : 01



MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES) TEST RESULTS FOR FINENESS MODULUS (F.M.) OF SAND

Job No : 10/2020-2021(Sand).

Name of Client : GE (Army) South, Dhaka.

Ref Itr No : 6000/Misc/68/E-6 Dt.20 July'2020.

Project Name : CEA/414 of 2019-2020.

Sample Specimen : Sylhet Sand.

Date of Sample Collection : Monday, 20 July, 2020

Sieve Size	Wt of Material Retained (gms)	Percentage Matarial Retained (rounded)	Cumulative % Retained	% Finer	Remarks
#4	3.56	0.89	0.89		
#8	25.46	6.37	7.26		
#16	93.87	23.47	30.72		
#30	169.53	42.38	73.11		
#50	86.04	21.51	94.62		FM = 3.06
#100	17.65	4.41	99.03		
#200	2.85	0.71	••••		
Pan	0.84	0.21			
			$\Sigma = 305.62$		

Cautions:

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secured and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1. 2.

Laboratory Technichian

Test Performed By

Vetted By

This is a computer genarated copy

No signature is required

Permissible Value:

- 1.For Sylhet/Domar Sand minimum FM will be = 2.50
- 2.For Local Sand minimum FM will be = 1.50
- 3. For Vitty Sand minimum FM will be = 0.80