

MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES)

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 69/2020-2021(Steel). Copy No. : 04

Name of Client : GE (Air) Chattogram. Sample Specimen : Length 600 mm Dia 25mm

Ref Itr No : 6004/ATI/24/E-6 Dt. 10 Sept'2020. Sample Grade : 60

Project Name : EinC/20 of 2017-2018. Frog Mark : Golden Ispat B-400 DWR

Date of Collection : Monday, 14 September, 2020

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	% (g	gation gauge gth)	ge Elongation	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.984 25	0.986 25.044	0.7609 490.8739	2.599 3.867		52870.82 235.18	69489 479		77635.89 345.34	102038 703		23			
2	0.984 25	0.986 25.044	0.7609 490.8739	2.599 3.867	2.599 3.867	52870.82 235.18	69489 479	69897 482	77536.97 344.9	101908 703	102068 704	27		25	
3	0.984 25	0.986 25.044	0.7609 490.8739	2.599 3.867		53803.78 239.33	70715 488		77804.49 346.09	102259 705		23.5			

Cautions:

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu	m Standard	Requiremen	nts (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a)									
6935-2:1991(E)				ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
Grade	Y/strength					Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)			GL (%)
	N/mm2 or	Control of the Contro	2000		psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36
	Mpa	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm		mm	mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	1000	7	7	6

This is a computer genarated copy

No signature is required

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi]

Laboratory Technichian

Test Performed By

Vetted By