

MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No
Name of Client
Ref Itr No
Project Name
Date of Collection

: 69/2020-2021(Steel). : GE (Air) Chattogram. : 6004/ATI/24/E-6 Dt. 10 Sept'2020. : EinC/20 of 2017-2018.

: Monday, 14 September, 2020

Copy No.
Sample Specimen
Sample Grade
Frog Mark

: 01

: Length 600 mm Dia 10mm

: 60

: Golden Ispat B-400 DWR

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	% (g	gation gauge gth)	uge Elonga	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.394 10	0.397 10.085	0.1217 78.5398	0.421 0.627		9021.63 40.13	74108 511		12200.44 54.27	100220 691		21			
2	0.394 10	0.397 10.085	0.1217 78.5398	0.421 0.627	0.421 0.627	9100.31 40.48	74754 515	74606 514	12200.44 54.27	100220 691	100349 692	18.5		20	
3	0.394 10	0.397 10.085	0.1217 78.5398	0.421 0.627		9125.04 40.59	74957 517		12247.65 54.48	100608 694		19.5			

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu		Requiremer 2:1991(E)	nts (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a) ASTM A 615 M ASTM A 615 M ASTM A 615/A 615 M									This is a computer genarated copy	
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum El	ongation in 8"(2	203.2 mm)	GL (%)	No signature is required
	N/mm2 or Mpa	N/mm2 or Mpa	%		psi (kg/cm2)	psi (kg/cm2)		Mpa (kg/cm2)	Mpa (kg/cm2)	10 mm	13,16,19 mm	22,25 mm	29,32,36 mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		110	
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note :[1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian Test Performed By

Vetted By