

# MATERIAL TESTING LABORATORY MILITARY ENGINEER SERVICES (MES)

## TEST RESULTS FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

2021(Con).		
Cox's Bazar.	Copy No.	: 01
76 of 2019-2020/25/E-6 Dt. 21 June'2021.	Sample Specimen	: HT 200mm (8"), Dia 100mm (4")
76 of 2019-2020.	Type of Aggregate	: Stone
oof.	Brand & Type of Cement	: Confidence opc
y, 23 June, 2021	Proportion of Mixture	: 1:1.25:2.5
	Desired Design Strength	: 2700 psi
7 1 n	-2021(Con). Cox's Bazar. 76 of 2019-2020/25/E-6 Dt. 21 June'2021. 176 of 2019-2020. roof. ay, 23 June, 2021 S	Cox's Bazar.Copy No.76 of 2019-2020/25/E-6 Dt. 21 June'2021.Sample Specimen176 of 2019-2020.Type of Aggregateroof.Brand & Type of Cementay, 23 June, 2021Proportion of Mixture

Ser No	Date of Casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs.)	Crushing Strength (psi)	Average Crushing Strength (psi)	Type of Failure
1			12.17	45119	3707		
2	19-Jun-21 (7 days)	26-Jun-21	12.17	61002	5012	4456	Aggregate/ Morter or Both Failure
3			12.17	56585	4650		

#### **Cautions:**

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

### **Observation on Specimen(if any):**

1.

Laboratory Technichian

Test Performed By

Vetted By

This is a computer genarated copy No signature is required

## **Permissible Value:**

Note :[1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi]