

MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES)

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 03/2021-2022(Steel) Copy No. : 01

Name of Client : GE (Army) Sylhet. Sample Specimen : Length 600 mm Dia 10mm

Ref Itr No : CEA/262 of 2020-2021/13/E-6 Dt. 24 June'2021. Sample Grade : 60

Project Name : CEA/262 of 2020-2021. Date of Collection : Thursday, 08 July, 2021 Frog Mark : Baizid B-420 DWR

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	% (g	gation gauge gth)	Elong % (g	rage gation gauge gth)
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.394 10	0.399 10.125	0.1217 78.5398	0.425 0.632		7481.68 33.28	61458 424		11818.26 52.57	97081 669		17.5			
2	0.394 10	0.399 10.125	0.1217 78.5398	0.425 0.632	0.425 0.632	7495.17 33.34	61569 424	64289 443	12288.11 54.66	100940 696	99303 685	19.5		18	
3	0.394 10	0.399 10.125	0.1217 78.5398	0.425 0.632		8502.31 37.82	69842 481		12159.97 54.09	99887 689		17.5			

Cautions:

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu	m Standard	Requiremen	nts (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a)									
	6935-	2:1991(E)		ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%			GL (%)
	N/mm2 or	CONTRACTOR OF THE PARTY OF THE	70275		psi	psi		Мра	Mpa	10	13,16,19 mm	22,25	29,32,36
	Mpa	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm		mm	mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6

This is a computer genarated copy

No signature is required

Note :[1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi]

Laboratory Technichian

Test Performed By

Vetted By