

MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No Name of Client Ref Itr No Project Name Date of Collection : 04/2021-2022(Steel)

: GE (Army) Sylhet.

: CEA/364 of 2020-2021/04/E-6 Dt. 24 June'2021.

: CEA/364 of 2020-2021.

: Thursday, 08 July, 2021

Copy No. Sample Specimen Sample Grade Frog Mark

: 01

: Length 600 mm Dia 10mm

: 60

: Baizid B-420 DWR

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength		gation gauge gth)	Elong % (g	erage gation gauge gth)
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.394 10	0.399 10.137	0.1217 78.5398	0.426 0.634		9358.84 41.63	76878 530		13081.69 58.19	107459 741		20.5			
2	0.394 10	0.399 10.137	0.1217 78.5398	0.426 0.634	0.426 0.634	9509.46 42.3	78115 539	77069 531	13164.87 58.56	108142 746	108093 745	20.5		20	
3	0.394 10	0.399 10.137	0.1217 78.5398	0.426 0.634		9277.91 41.27	76213 525		13230.07 58.85	108678 749		19			

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu		Requiremer 2:1991(E)	nts (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a) ASTM A 615 M ASTM A 615 M ASTM A 615/A 615 M										This is a computer genarated copy
Grade	Grade Y/strength Ult.Str Elongation		Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)			GL (%)	No signature is required	
	N/mm2 or Mpa	N/mm2 or Mpa	%		psi (kg/cm2)	psi (kg/cm2)		Mpa (kg/cm2)	Mpa (kg/cm2)	10 mm	13,16,19 mm	22,25 mm	29,32,36 mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian Test Performed By

Vetted By