

MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES)

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 04/2021-2022(Steel) Copy No. : 02

Name of Client : GE (Army) Sylhet. Sample Specimen : Length 600 mm Dia 12mm

Ref Itr No : CEA/364 of 2020-2021/04/E-6 Dt. 24 June'2021. Sample Grade : 60

Project Name : CEA/364 of 2020-2021. Date of Collection : Thursday, 08 July, 2021

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	Elongation % (gauge length)		Elong % (ga	Average Elongation % (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**	
1	0.472 12	0.474 12.028	0.1753 113.0973	0.599 0.892	0.599 0.892	13007.51 57.86	74201 512		17211.45 76.56	98182 677	98328 678	17.5		16		
2	0.472 12	0.474 12.028	0.1753 113.0973	0.599 0.892		13241.31 58.9	75535 521	75090 518	17487.97 77.79	99760 688		16				
3	0.472 12	0.474 12.028	0.1753 113.0973	0.599 0.892		13241.31 58.9	75535 521		17011.37 75.67	97041 669		14.5	;			

Cautions:

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Minimu	m Standard I	Requiremen	nts (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a)									
	6935-2	2:1991(E)		ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
Grade	Y/strength	//strength Ult.Str E		Grade	Y/strength	ength Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)			
	N/mm2 or Mpa	N/mm2 or Mpa	%		psi (kg/cm2)	psi (kg/cm2)		Mpa (kg/cm2)	Mpa (kg/cm2)	10 mm	13,16,19 mm	22,25 mm	29,32,36 mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		(100)
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6

This is a computer genarated copy

No signature is required

: Baizid B-420 DWR

Note: [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian

Test Performed By

Frog Mark

Vetted By