



# MATERIAL TESTING LABORATORY

## MILITARY ENGINEER SERVICES (MES)

### TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No	: 10/2021-2022(Steel)	Copy No.	: 03
Name of Client	: GE(Army) Chattogram.	Sample Specimen	: Length 600 mm Dia 16mm
Ref Itr No	: CEA/697 of 2019-2020/10/E-6 Dt.14July'2021	Sample Grade	: 60
Project Name	: CEA/697 of 2019-2020	Frog Mark	: RSMB420 DWR
Date of Collection	: Sunday, 18 July, 2021		

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	Elongation % (gauge length)		Average Elongation % (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.63 16	0.633 16.071	0.3116 201.0619	1.07 1.592	1.07 1.592	21114.16 93.92	67750 467	69208 477	30066.09 133.74	96475 665	96845 668	19		17	
2	0.63 16	0.633 16.071	0.3116 201.0619	1.07 1.592		21725.64 96.64	69713 481		30306.64 134.81	97247 670		15.5			
3	0.63 16	0.633 16.071	0.3116 201.0619	1.07 1.592		21865.02 97.26	70160 484		30171.75 134.21	96814 667		15			

#### Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the samples to be tested.
2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

#### Observation on Specimen(if any):

- 1.

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E))				Minimum Standard Requirements (ASTM A615/A616M-96a)									
Grade	Y/strength	Ult.Str	Elongation	ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
	N/mm2 or Mpa	N/mm2 or Mpa	%	Grade	Y/strength psi (kg/cm2)	Ult.Str psi (kg/cm2)	Grade	Y/strength Mpa (kg/cm2)	Ult.Str Mpa (kg/cm2)	Minimum Elongation in 8"(203.2 mm) GL (%)			
										10 mm	13,16,19 mm	22,25 mm	29,32,36 mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12	..	..
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	..	7	7	6

This is a computer generated copy  
No signature is required

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi]

Laboratory Technician

Test Performed By

Vetted By