

MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No Name of Client Ref Itr No Project Name Date of Collection : 09/2021-2022(Steel).

: AGE(Air) Cox's Bazar.

: CE Air/176 of 2019-2020/28/E-6 Dt.15 July'2021

: CE Air/176 of 2019-2020

: Sunday, 18 July, 2021

Copy No.	
Sample Specimen	
Sample Grade	
Frog Mark	

: 03 : Length 600 mm Dia 16mm

: 60

: Baizid 420

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	ate % (gauge		Elong % (g	erage gation gauge gth)
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.63 16	0.636 16.163	0.3116 201.0619	1.082 1.611		22566.43 100.38	72410 499		29870.5 132.87	95848 661		17			
2	0.63 16	0.636 16.163	0.3116 201.0619	1.082 1.611	1.082 1.611	22566.43 100.38	72410 499	72475 500	29656.94 131.92	95162 656	95576 659	18.5		18	
3	0.63 16	0.636 16.163	0.3116 201.0619	1.082 1.611		22627.13 100.65	72605 501		29830.04 132.69	95718 660		19.5			

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu		Requiremer 2:1991(E)	nts <mark>(BDS/I</mark> SO	Minimum Standard Requirments(ASTM A615/A616M-96a)ASTM A 615 MASTM A 615 MASTM A 615 MASTM A 615/A 615 M										This is a computer genarated copy
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum E	ongation in 8"(2	.03.2 mm)	GL (%)	No signature is required
	N/mm2 or Mpa	N/mm2 or Mpa	%		psi (kg/cm2)	psi (kg/cm2)		Mpa (kg/cm2)	Mpa (kg/cm2)	10 mm	13,16,19 mm	22,25 mm	29,32,36 mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian Test Performed By

Vetted By