

### MATERIAL TESTING LABORATORY

# MILITARY ENGINEER SERVICES (MES) TEST RESULTS FOR FINENESS MODULUS (F.M.) OF SAND

Job No : 20/2021-2022(Sand).

Name of Client : GE (Army) South, Dhaka. Copy No : 02

Ref Itr No : 6000/Misc/15/E-6 Dt. 18 Aug'2021.

Project Name : CEA/539 of 2020-2021.

Sample Specimen : Local Sand.

Date of Sample Collection : Wednesday, 25 August, 2021

Sieve Size	Wt of Material Retained (gms)	Percentage Matarial Retained (rounded)	Cumulative % Retained	% Finer	Remarks
#4	0	0	0		
#8	0.14	0.04	0.04		
#16	0.16	0.04	0.08		
#30	3.52	0.88	0.96		
#50	211.97	52.99	53.95		FM = 1.51
#100	166.37	41.59	95.54		
#200	15.08	3.77	<b></b>		
Pan	2.01	0.5	····		
			$\Sigma = 150.55$		

#### **Cautions:**

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secured and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

## **Observation on Specimen(if any):**

1.

2.

<u>Laboratory Technichian</u> <u>Test Performed By</u> <u>Vetted By</u>

This is a computer genarated copy

No signature is required

# Permissible Value:

- 1.For Sylhet/Domar Sand minimum FM will be = 2.50
- 2.For Local Sand minimum FM will be = 1.50
- 3. For Vitty Sand minimum FM will be = 0.80