

MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No
Name of Client
Ref Itr No
Project Name
Date of Collection

: GE (Army) South, Dhaka. : 6000/Misc/23/E-6 Dt. 22 Aug'2021. : CEA/735 of 2020-2021. : Monday, 23 August, 2021

: 29/2021-2022(Steel).

Copy No.	:
Sample Specimen	:
Sample Grade	:
Frog Mark	:

05 Length 600 mm Dia 25mm 60

AKS 500 W

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength		gation auge gth)	Ave Elon % (g len
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch
1	0.984 25	0.985 25.009	0.7609 490.8739	2.591 3.857		61948.64 275.56	81420 561		75097.78 334.05	98702 680		23.5		
2	0.984 25	0.985 25.009	0.7609 490.8739	2.591 3.857	2.591 3.857	61640.65 274.19	81015 559	81086 559	75945.31 337.82	99816 688	99107 683	23		23
3	0.984 25	0.985 25.009	0.7609 490.8739	2.591 3.857		61494.53 273.54	80823 557		75174.22 334.39	98802 681		22.5		

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu	Minimum Standard Requirements (BDS/ISO Minimum Standard Requirments(ASTM A615/A616M-96a)													
	6935-	2:1991(E)			ASTM A 61	M ASTM A 615 M ASTM A 615/A 615 M					This is a computer genarated copy			
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum El	ongation in 8"(2	203.2 mm)	GL (%) No signature is require	No signature is required
	N/mm2 or	Contraction of the second	22.36		psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36	
	Mpa	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm		mm	mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian

Test Performed By

Vetted By