

MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES)

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 36/2021-2022(Steel) Copy No. : 02

Name of Client : AGE (Army) Jahanabad. Sample Specimen : Length 600 mm Dia 12mm

Yield or

Proof

Strength

psi

Mpa

70995

489

72175

498

68879

475

Yield or

Proof Load

lb

kn

12445.48

55.36

12652.31

56.28

12074.55

53.71

Ref Itr No : 6000/Test/07/E-6 Dt. 25 Aug'2021. Sample Grade : 60

Average

Actual Ŭnit

Weight

lb/ft

kg/m

0.598

0.89

Project Name : EinC/172 of 2020-2021. Date of Collection : Sunday, 29 August, 2021

Actual Dia

inch

mm

0.473

12.016

0.473

12.016

0.473

12.016

Area Under

Test

sq.inch

sq.mm

0.1753

113.0973

0.1753

113.0973

0.1753

113.0973

Actual Unit

Weight

lb/ft

kg/m

0.598

0.89

0.598

0.89

0.598

0.89

Elongation Average Ultimate Ultimate Average Average Yield or Load Ultimate Elongation Strength % (gauge Proof length) Strength % (gauge Strength length) 8inch | 5d** 8inch | 5d** lb psi psi psi Mpa kn Mpa Mpa 16822.53 95964 16.5 74.83 662 17384.56 99170 97400 19.5 70683 18 77.33 671 487 684

97067

669

: Purbachal B-420 DWR.

16.5

Frog Mark

17015.87

75.69

Cau	4:	ma
Cau	II.IC	1115.

Sample

No

1

2

3

Nominal

Dia

inch

mm

0.472

12

0.472

12

0.472

12

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimum Standard Requirements (BDS/ISO		Minimum Standard Requirments(ASTM A615/A616M-96a)											
6935-2:1991(E)			ASTM A 615 M		ASTM A 615 M		ASTM A 615/A 615 M						
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)			
	N/mm2 or	Control of the Contro	32.8		psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36
	Mpa	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm	A 250	mm	mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		**
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	1344	7	7	6

This is a computer genarated copy

No signature is required

Note: [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian

Test Performed By

Vetted By