

MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No Name of Client Ref Itr No Project Name Date of Collection

: AGE (Army) Jahanabad. : 6000/Test/07/E-6 Dt. 25 Aug'2021. : EinC/172 of 2020-2021. : Sunday, 29 August, 2021

: 36/2021-2022(Steel)

Copy No. Sample Specimen Sample Grade Frog Mark

: 03

: Length 600 mm Dia 16mm

: 60

: Purbachal B-420 DWR.

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	% (g	gation gauge gth)		
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.63 16	0.631 16.037	0.3116 201.0619	1.066 1.586		23434.19 104.24	75195 518		31498.13 140.11	101070 697		22			
2	0.63 16	0.631 16.037	0.3116 201.0619	1.066 1.586	1.066 1.586	23730.94 105.56	76147 525	74584 514	31392.47 139.64	100731 694	99654 687	16.5		18	
3	0.63 16	0.631 16.037	0.3116 201.0619	1.066 1.586		22566.43 100.38	72410 499		30279.66 134.69	97160 670		16.5			

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu	Minimum Standard Requirements (BDS/ISO				Minimum Standard Requirments(ASTM A615/A616M-96a)									
6935-2:1991(E)			ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M				This is a computer genarated copy	
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)			GL (%)	No signature is required
	N/mm2 or	Contraction of the second second	22-25		psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36	
	Мра	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm		mm	mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian Test Performed By

Vetted By