

MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES) TEST RESULTS FOR FINENESS MODULUS (F.M.) OF SAND

Job No : 60/2021-2022 (Sand).

Name of Client : GE (Navy) Khulna. Copy No : 01

Ref Itr No : CEN/72 of 2020-2021/10/E-6 Dt. 07 Oct'2021.

Project Name : CEN/72 of 2020-2021

Sample Specimen : Sylhet Sand.

Date of Sample Collection : Monday, 11 October, 2021

Sieve Size	Wt of Material Retained (gms)	Percentage Matarial Retained (rounded)	Cumulative % Retained	% Finer	Remarks
#4	3.59	0.9	0.9		
#8	21.91	5.48	6.38		
#16	104.59	26.15	32.52		
#30	140.1	35.03	67.55		
#50	80.12	20.03	87.58		FM = 2.91
#100	35.8	8.95	96.53		
#200	11.42	2.86			
Pan	2.09	0.52			
			$\Sigma = 291.45$		

Cautions:

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secured and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

2.

Laboratory Technichian Test Performed By Vetted By

This is a computer genarated copy

No signature is required

Permissible Value:

- 1.For Sylhet/Domar Sand minimum FM will be = 2.50
- 2.For Local Sand minimum FM will be = 1.50
- 3. For Vitty Sand minimum FM will be = 0.80