

MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES) TEST RESULTS FOR FINENESS MODULUS (F.M.) OF SAND

Job No : 60/2021-2022 (Sand).

Name of Client : GE (Navy) Khulna. Copy No : 02

Ref Itr No : CEN/72 of 2020-2021/10/E-6 Dt. 07 Oct'2021.

Project Name : CEN/72 of 2020-2021

Sample Specimen : Local Sand.

Date of Sample Collection : Monday, 11 October, 2021

Sieve Size	Wt of Material Retained (gms)	Percentage Matarial Retained (rounded)	Cumulative % Retained	% Finer	Remarks
#4	0	0	0		
#8	1.34	0.34	0.34		
#16	0.91	0.23	0.56		
#30	7.54	1.89	2.45		
#50	134.34	33.59	36.03		FM = 1.32
#100	227.25	56.81	92.85		
#200	25.01	6.25			
Pan	2.6	0.65			
			$\Sigma = 132.22$		

Cautions:

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secured and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.As the result is below the std.value, so nec, measures to be taken as per particular specification of contract.

2.

Laboratory Technichian

Test Performed By

Vetted By

This is a computer genarated copy

No signature is required

Permissible Value:

- 1.For Sylhet/Domar Sand minimum FM will be = 2.50
- 2.For Local Sand minimum FM will be = 1.50
- 3. For Vitty Sand minimum FM will be = 0.80