

MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES) TEST RESULTS FOR FINENESS MODULUS (F.M.) OF SAND

Job No : 02/2022-2023(Sand).

Name of Client : GE (Army) North, Dhaka. Copy No : 02

Ref Itr No : CEA/381 of 2021-2022/06/E-6 Dt. 23 Jun'2022.

Project Name : CEA/381 of 2021-2022.

Sample Specimen : Local Sand.

Date of Sample Collection : Sunday, 03 July, 2022

Sieve Size	Wt of Material Retained (gms)	Percentage Matarial Retained (rounded)	Cumulative % Retained	% Finer	Remarks
#4	0	0	0		
#8	3.09	0.77	0.77		
#16	39.28	9.82	10.59		
#30	252.41	63.1	73.7		
#50	100.77	25.19	98.89		FM = 2.83
#100	2.06	0.52	99.4		
#200	1.4	0.35			
Pan	0.55	0.14			
			$\Sigma = 283.35$		

Cautions:

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secured and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

2.

Laboratory Technichian Test Performed By Vetted By

This is a computer genarated copy

No signature is required

Permissible Value:

- 1.For Sylhet/Domar Sand minimum FM will be = 2.50
- 2.For Local Sand minimum FM will be = 1.50
- 3. For Vitty Sand minimum FM will be = 0.80