

# MATERIAL TESTING LABORATORY

#### MILITARY ENGINEER SERVICES (MES)

#### TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No : 07/2022-2023 (Steel). Copy No. : 03

Name of Client : GE (Army) North Dhaka. Sample Specimen : Length 600 mm Dia 16mm

Ref Itr No : CEA/381 of 2021-2022/08/E-6 Dt.05 Jul'2022. Sample Grade : 60

Project Name : CEA/381 of 2021-2022.
Date of Collection : Wednesday, 06 July, 2022

Area Under Actual Dia Yield or Yield or Elongation Sample Nominal Actual Unit Average Average Ultimate Ultimate Average Average No Test Weight Actual Ŭnit **Proof Load** Proof Yield or Load Ultimate Elongation Dia Strength % (gauge Weight Proof length) Strength Strength % (gauge Strength length) 8inch | 5d\*\* 8inch | 5d\*\* inch inch lb/ft lb/ft lb lb sq.inch psi psi psi psi mm mm sq.mm kg/m kg/m kn Mpa Mpa kn Mpa Mpa 19 1 0.63 0.637 0.3116 1.083 22433.79 71985 30419.04 97608 16 16.168 201.0619 1.612 99.79 496 135.31 673 2 0.63 21777.34 28296.83 93227 19 0.637 0.3116 1.083 1.083 69878 70446 90798 18 482 643 16 16.168 201.0619 1.612 1.612 96.87 486 125.87 626 3 17 0.63 0.637 0.3116 1.083 21651.45 69475 28445.21 91274 16 16.168 201.0619 1.612 96.31 479 126.53 629

## **Cautions:**

- 1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.
- 2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
- 3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

### **Observation on Specimen(if any):**

1.

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E)				Minimum Standard Requirments(ASTM A615/A616M-96a)									
				ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)			
	N/mm2 or	Control of the Contro	32.8		psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36
	Mpa	Mpa	%		(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm	A 250	mm	mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		**
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	1344	7	7	6

This is a computer genarated copy

No signature is required

: Baizid B-420 DWR

Note: [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] La

Laboratory Technichian

Test Performed By

Frog Mark

Vetted By