

MATERIAL TESTING LABORATORY **MILITARY ENGINEER SERVICES (MES)**

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No Name of Client Ref Itr No Project Name Date of Collection

: GE (Army) North Dhaka. : CEA/381 of 2021-2022/08/E-6 Dt.05 Jul'2022. : CEA/381 of 2021-2022.

: 07/2022-2023 (Steel).

: Wednesday, 06 July, 2022

Copy No.
Sample Specimen
Sample Grade
Frog Mark

: 02

: Length 600 mm Dia 12mm

: 60

: Baizid B-420 DWR

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	Elong % (g leng		Average Elongation % (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.472 12	0.482 12.236	0.1753 113.0973	0.62 0.923		12937.82 57.55	73803 509		17454.25 77.64	99567 686		20.5			
2	0.472 12	0.482 12.236	0.1753 113.0973	0.62 0.923	0.62 0.923	12416.26 55.23	70828 488	72260 498	17580.14 78.2	100286 691	99076 683	20		20	
3	0.472 12	0.482 12.236	0.1753 113.0973	0.62 0.923		12647.81 56.26	72149 497		17069.82 75.93	97374 671		20.5			

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecter of the samples to be tested.

2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.

3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimu	m Standard	Requiremer	nts (BDS/ISO	Minimum Standard Requirments(ASTM A615/A616M-96a)										
6935-2:1991(E)			ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M				This is a computer genarated copy	
Grade	Y/strength	Ult.Str	Elongation	Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum El	ongation in 8"(2	203.2 mm) (GL (%)	No signature is required
	N/mm2 or	Contraction of the second	22.35	3	psi	psi		Mpa	Mpa	10	13,16,19 mm	22,25	29,32,36	
	Мра	Мра	%	· · · · · · · · · · · · · · · · · · ·	(kg/cm2)	(kg/cm2)		(kg/cm2)	(kg/cm2)	mm		mm	mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12			
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7	
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)		7	7	6	

Note :[1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi] Laboratory Technichian Test Performed By

Vetted By