



MATERIALS TESTING LABORATORY MILITARY ENGINEER SERVICES(MES)

TEST RESULT FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S BARS

Job No : 50/2022-2023(Steel)	Copy No : 03
Name of Client : GE (Army) Sylhet	Sample Specimen : Length 600mm , Dia 16mm
Ref.ltr.No : CEA/16 of 2021-2022/29/E-6 Dt.22 Aug'2022	Sample Grade : 60
Project Name : Construction of Water Reservoir & Pump House.	Frog Mark : BSRM Ultima 420 D
Dt. of Sample Collection: 30 Aug '2022	

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof load	Yield or Proof Strength	Average Yield or Proof load	Ultimate load	Ultimate Strength	Average Ultimate Strength	Ratio (Fult/Fy)	Elongation% (gauge length)		Average Elongation% (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa		8inch	5d	8inch	5d
1	0.630	0.621	0.312	1.030	1.030	20481.56	65720	66486	29035.66	93169	93085	1.42	25.5	23		
	16.00	15.765	201.062	1.532		91.11	453		129.16	643						
2	0.630	0.621	0.312	1.030		1.532	20719.37		66484	66486		28784.00	92361			
	16.00	15.765	201.062	1.532	92.16	459	128.04	637								
3	0.630	0.621	0.312	1.030	1.030	20959.49	67254	66486	29208.82		93724	93085	1.39	22	23	
	16.00	15.765	201.062	1.532		93.23	464		129.93	646						

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecture of the samples to be tested.
2. It is recommended that samples are Sent in asecuried and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent of the test results,it is recommended that all test reports should be collected by duly authorised person and not by contractor/supplier.

Oservation on Specimen(if any):

1. Diameter & Unit weight of 16 mm bar is less than the standard value but within tolerance limit according to MES Schedule of Rates-2016.

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E))				Minimum Standard Requirments(ASTM A615/A616M-96a)												
Grade	Y/strength	Ult.Str	Elongation	ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M						
				Grade	Y/strength	Ult.Str	Grade	Y/strength	Ult.Str	Minimum Elongation in 8"(203.2 mm) GL (%)						
	Mpa	Mpa	%		(kg/cm2)	psi		Mpa	(kg/cm2)	(kg/cm2)	10	13,16,19	mm	22,25	mm	29,32,36
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12		
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9			8		7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	..	7			7		6

Laboratory Technician

Test Performed By

Vetted By