



MATERIALS TESTING LABORATORY MILITARY ENGINEER SERVICES(MES)

TEST RESULT FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S BARS

Job No : 137/2022-2023(Steel)	Copy No : 05
Name of Client : GE (Army) South,Dhaka.	Sample Specimen : Length 600mm , Dia 25mm
Ref.ltr.No : 6000/Misc/61/E-6 Dt. 31 Oct'2022.	Sample Grade : 60
Project Name : Construction of 1 x 52 (C/D Type) Officer's Qtr.	Frog Mark : RSM B 400 B-R.
Dt. of Sample Collection: 01 Nov'2022	

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof load	Yield or Proof Strength	Average Yield or Proof load	Ultimate load	Ultimate Strength	Average Ultimate Strength	Ratio (Fult/Fy)	Elongation% (gauge length)		Average Elongation% (gauge length)				
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa		8inch	5d	8inch	5d			
1	0.984 25.00	0.986 25.046	0.7609 490.8739	2.599 3.868	2.599 3.868	52449.19 233.30	68934 475	67714 467	64882.07 288.61	85275 588	84930 586	1.24	24.5		24				
2	0.984 25.00	0.986 25.046	0.7609 490.8739	2.599 3.868		51874.30 230.75	68179 470		64752.78 288.03	85105 587							1.25	22.5	
3	0.984 25.00	0.986 25.046	0.7609 490.8739	2.599 3.868		50237.36 223.47	66027 455		64224.06 285.68	84410 582							1.28	24.5	

Cautions:

1. Samples as supplied to the laboratory have been tested.The laboratory authority does not bear any responsibility as to the representative charecture of the samples to be tested.
2. It is recommended that samples are Sent in asecuried and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent of the test results,it is recommended that all test reports should be collected by duly authorised person and not by contractor/supplier.

Ovservation on Specimen(if any):

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E))				Minimum Standard Requirments(ASTM A615/A616M-96a)									
Grade	Y/strength	Ult.Str	Elongation	ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
	N/mm2 or Mpa	N/mm2 or Mpa	%	Grade	Y/strength psi (kg/cm2)	Ult.Str psi (kg/cm2)	Grade	Y/strength Mpa (kg/cm2)	Ult.Str Mpa (kg/cm2)	Minimum Elongation in 8"(203.2 mm) GL (%)			
										10 mm	13,16,19 mm	22,25 mm	29,32,36 mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	..	7	7	6

Laboratory Technician

Test Performed By

Vetted By