



MATERIAL TESTING LABORATORY
MILITARY ENGINEER SERVICE(MES)

Page No : 279

Copy no : 01

TEST RESULT FOR COMPRESSIVE STRENGTH OF CONCRETE CYLINDER/CUBE

Job No : 200/2023-2024 (Con).
Name of Client : GE (Air) Tejgaon,Dhaka.
Ref ltr no : CE Air/251 of 2022-2023/29/E-6 Dt.15 Oct' 2023.
Name of the project : Construction of BOQ.
Status of sample : Pre cast pile.
Dt of sample collection: 15 Oct'2023
Test Standard : ASTM/BS

Sample Specimen: Ht 200mm(8") Dia 100 mm(4")
Type of Aggregate : Stone
Brand &Type of Cement : Akij Opc.
Proportion of Mixture : 1:1.25:2.5
Desired Design Strength : 2800 Psi

Ser no.	Date of casting and (Age in days)	Date of Test	Specimen Area Sq inch	Maximum Load (Lbs)	Crushing Strength (Psi)	Average Crushing Strength (Psi)	Remarks
1	10 Oct '2023 (07 days)	17 Oct'2023	12.17	74113.67	6090	Average of Sample 2 & 3 5233	Combined Failure
2			12.17	66644.81	5476		
3			12.17	60720.44	4989		

Cautions :

- 1 Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the sample to be tested.
- 2 It is recommended that samples are sent in a sealed cover/packet/container under signature of the competent authority
- 3 In order to be avoid fraudulent fabrication of the test result ,it is recommended that test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1

Laboratory Technician

Test Performed By

Vetted By

Note:[1 Mpa=145 psi, 1kg/cm²=14.223 Psi]