



MATERIALS TESTING LABORATORY MILITARY ENGINEER SERVICES(MES)

TEST RESULT FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S BARS

Job No : 88/2023-2024 (Steel).	Copy No : 05
Name of Client : GE (Army) Mirpur.	Sample Specimen : Length 600mm , Dia 25mm
Ref.ltr.No : EinC/468 of 2022-2023/12/E-6 Dt.12 Oct'2023.	Sample Grade : 60
Project Name : Construction of 1 x 150 Officer's mess & 1 x 450 BOQ.	Frog Mark : RSM B-420 DWR.
Dt. of Sample Collection: 16 Oct'2023	

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof load	Yield or Proof Strength	Average Yield or Proof load	Ultimate load	Ultimate Strength	Average Ultimate Strength	Ratio (Fult/Fy)	Elongation% (gauge length)		Average Elongation% (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa		8inch	5d	8inch	5d
1	0.984 25.00	0.989 25.11	0.7609 490.8739	2.612 3.887	2.612 3.887	61292.22 272.64	80557 556	79741 550	81225.88 361.31	106756 736	107963 745	1.33	24	24		
2	0.984 25.00	0.989 25.11	0.7609 490.8739	2.612 3.887		61287.59 272.62	80551 556		82375.59 366.42	108267 747		1.34	23.5			
3	0.984 25.00	0.989 25.11	0.7609 490.8739	2.612 3.887		59434.64 264.38	78115 539		82831.31 368.45	108866 751		1.39	25.5			

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative charecture of the samples to be tested.
2. It is recommended that samples are Sent in asecuried and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent of the test results, it is recommended that all test reports should be collected by duly authorised person and not by contractor/supplier.

Oservation on Specimen(if any):

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E))				Minimum Standard Requirments(ASTM A615/A616M-96a)										
Grade	Y/strength	Ult.Str	Elongation	ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M				
	N/mm2 or Mpa	N/mm2 or Mpa	%	Grade	Y/strength psi (kg/cm2)	Ult.Str psi (kg/cm2)	Grade	Y/strength Mpa (kg/cm2)	Ult.Str Mpa (kg/cm2)	Minimum Elongation in 8"(203.2 mm) GL (%)				
										10 mm	13,16,19 mm		22,25 mm	29,32,36 mm
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12	
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9		8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	..	7		7	6

Laboratory Technician

Test Performed By

Vetted By